



Salt Spray Corrosion Test Chamber

-----Internal dimension can be customized

-----Continuous and programmable spraying

Model	SH-60	SH-90	SH-120	SH-160	SH-200
Internal Dimension WxHxD (mm)	600x450x400	900x600x500	1200x800x500	1600x800x500	2000x1000x500
External Dimension WxHxD (mm)	1100x600x1200	1400x950x1200	1900x1300x1400	2300x1300x1400	2700x1500x1500
Lab Temperature	Saline test (NSS ACSS) 35±1 °C / Corrosion Test (CASS) 50±1 °C				
Pressure Bucket Temperature	Saline test method (NSS ACSS) 47±1 °C / Corrosion Test (CASS) 63±1 °C				
Lab Capacity(L)	110	270	500	800	1500
Saline Capacity(L)	15	25	40	40	40
Saline Concentration	5% concentration of NaCl, or every Liter 5% NaCl add 0.26g CuCl ₂ H ₂ O				
Compressed Air Pressure(Kgf)	1.0~6.0				
Spray Volume	1.0~2.0ml /80cm ² /h (working at least 16 hours, and take the average value)				
Spray Form	Continuous Spraying or Programmable Spraying				
Power	AC 220V, 1 φ 3 lines 15A				
Weight(Kg)	65	80	120	160	200

Pictures for reference:

